

PATENT ABSTRACTS OF JAPAN

(11)Publication number : **08-034882**

(43)Date of publication of application : **06.02.1996**

(51)Int.Cl.

C08L 23/06
C08J 5/18
C08K 5/10

(21)Application number : **06-170944**

(71)Applicant : **SEKISUI CHEM CO LTD**

(22)Date of filing : **22.07.1994**

(72)Inventor : **KUSU TAKAYUKI
TANIGUCHI NOBUO**

(54) **ANTI-FOGGING FILM**

(57)Abstract:

PURPOSE: To provide a film which has excellent anti-fogging properties even in low-temp. storage and retains transparency, pliability, and stretchability, and the extrusion molding of which is free from slip in the barrel by incorporating an adequate antifogging agent into linear low-density polyethylene.

CONSTITUTION: The film is made from a resin composition comprising 100 pts.wt. linear polyethylene having a density of 0.920g/cm³ or lower, 1-5 pts.wt. diglycerol laurate, and 10-30 pts.wt. low-density polyethylene.

LEGAL STATUS

[Date of request for examination] 30.11.2000

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3473993

[Date of registration] 19.09.2003

[Number of appeal against examiner's

* NOTICES *

JPO and INPIT are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] The fog resistance film with which a consistency consists of a resin constituent containing diglycerol laurate 1 - 5 weight sections, and low density polyethylene 10 - 30 weight sections to the three or less 0.920 gr/cm straight chain-like low-density-polyethylene 100 weight section.

[Claim 2] The fog resistance film with which a consistency consists of a resin constituent containing diglycerol laurate 1 - 5 weight sections, glycerol mono-olate 0.1 - 1 weight section, the polyoxyethylene sorbitan trio rate 0.1 - 1 weight section, polyoxyethylene alkyl ether 0.1 - 1 weight section, and low density polyethylene 10 - 30 weight sections to the three or less 0.920 gr/cm straight chain-like low-density-polyethylene 100 weight section.

[Translation done.]